

**REGENERATED PET RESIN COMPOSITION**


Patent number: JP2003213112  
Publication date: 2003-07-30  
Inventor: OTOMO TAKASHI; KONO TOSHIYUKI; INOUE TAKASHI; KURIYAMA TAKU  
Applicant: YAMAGATA UNIV RES INST;; MIRAI KASEI KK;; SIGMA KK  
Classification:  
- international: C08L67/02; C08L23/00; C08L53/02; C08L51/00  
- european:  
Application number: JP20020020252 20020129  
Priority number(s): JP20020020252 20020129

Report a data error here

**Abstract of JP2003213112**

<P>PROBLEM TO BE SOLVED: To obtain a regenerated PET resin composition using a ground product of a PET product such as waste PET bottles, or the like, the composition controlling a deterioration by a hydrolysis, being suitable for extrusion molding and having excellent mechanical characteristics.

<P>SOLUTION: The regenerated PET resin composition is obtained by kneading (A) 100 pts.wt. of the PET ground product of a used waste PET product, (B) 3-60 pts.wt. of a polyolefin resin, (C) 2-80 pts.wt. of a block copolymer having a block comprising at least one vinyl aromatic compound polymer and another block comprising at least one conjugated diene compound polymer, and (D) 150 pts.wt. of a multi-layer structure polymer obtained by graft copolymerization of an olefin copolymer containing an epoxy group and a vinyl (co)polymer, in kneading equipment at a temperature of from at least the melting point of the component (B) (the polyolefin resin) to lower than the melting point of component (A) (the PET ground product). <P>COPYRIGHT: (C)2003,JPO



BEST AVAILABLE COPY

Data supplied from the esp@cenet database - Worldwide